

## ARMOUR-GUARD PRIMER S

### Hard, very fast curing, PMMA based primer for Armour-Guard® Systems

Armour-Guard Primer S is a hard, very fast curing, PMMA (Polymethyl Methacrylate) based primer for Armour-Guard Systems, to be applied on mineral surfaces.

#### BENEFITS

- High reactivity
- Fast curing
- Applicable even at low temperature -25°C / -13°F
- Optimal viscosity, horizontal or vertical application
- Widely applicable, excellent adhesion to most substrates
- Optimized polymerization under difficult conditions
- Easy application with roller or brush

#### FIELD OF APPLICATION

Armour-Guard Primer S is a hard primer for the Armour-Guard floor, membrane and other Armour-Guard Systems that are applied to mineral, absorbent surfaces such as sand/cement screeds, concrete, brick, and prepared tiles. The primer has excellent adhesion and can be applied at temperatures below freezing thanks to its rapid curing and high reactivity. Armour-Guard Primer S can be used as concrete protection layer, and when fully broadcasted with sand, can be used as a fast curing primer for epoxy and polyurethane floor systems.

#### APPLICATION

**Note: The following is a typical application description. In case of other jobsite parameters, please contact a Transpo regional manager.**

##### Pre-application Checks

Before starting the substrate preparation and applying any Armour-Guard range of products, it is important to test various parameters in order to achieve an optimal and sustainable result.

Compressive strength of the substrate: minimum 25 N/mm<sup>2</sup> / 3,500 psi.

Tensile strength of the substrate: minimum 1.5 N/mm<sup>2</sup> / 220 psi.

Armour-Guard Primer S must be applied on a dry surface. Moisture content in the substrate should be ≤ 6% checked with Tramex CME5 or similar moisture encounter device.

Appropriate and correctly placed expansion joints must be provided where required and these should not be overcoated.

The flatness/slope of the surface must be consistent with the desired requirements. Should this not be the case, corrective measures must be taken to fill in or smooth out the unevenness with compatible products, such as Transpo T-17.

Shrinkage cracks and passive cracks can be coated provided they are not performing as expansion joints and they are isolated from other movements of the structure. They should be addressed and treated with products that are complementary to the substrate and to the Armour-Guard System to be installed.

##### Required Tools

- Mixer with spiral paddle (min. 300 rpm)
- Spatula or rubber squeegee
- Brush or paint roller suitable for synthetic resin-based products
- Masking tape

##### Preparation of the Substrate

Cracks, joints and other areas that show water leaks must first be made water-tight and leak-proof using products compatible with Armour-Guard Systems.

The surface must be mechanically prepared to CSP 4-6 / SSPC-SP 10 (NACE No. 2) by abrasive blasting, scarification, milling/micro-milling or other process providing that it achieves the required surface profile. Tiles are to be fully degreased and ground with a diamond blade. These treatments ensure that an open texture surface is obtained, to remove any laitance from concrete, and old remnants of coatings and adhesives. High pressure water jetting is possible but the surface must dry sufficiently (moisture content in the substrate: ≤ 6% moisture) before applying the primer.

Always apply the products on a clean surface, free from adhesion reducing materials and deleterious substances such as dirt, oil, grease, old coatings or surface treatments. Areas of the surfaces to be coated that do not meet the requirements as described above (compressive strength, tensile strength, parts that are not well connected) must be treated or removed and repaired according to a correct method and with products that are complementary to the substrate and the Armour-Guard System to be installed. Remove any loose parts by brushing properly and with compressed air/high-power leafblowers and remove dust with an industrial vacuum cleaner.

### Preparation of the Product

Mix Armour-Guard Primer S well before use, approximately 3 minutes with spiral type mixer as paraffin can separate during storage.

Dispense an appropriate amount of resin that can be processed within 15 minutes. Add 1% to 6% of Armour-Guard Catalyst curing powder depending on jobsite temperature conditions. Mix until completely dissolved. Armour-Guard Catalyst must be ordered separately.

Add Armour-Guard Catalyst to Armour-Guard Primer S

Temp.	In %	Armour-Guard Catalyst per 1kg Armour-Guard Primer S
0°C / 32°F	5%	50 g
5°C / 41°F	4%	40 g
10°C / 50°F	3%	30 g
20°C / 68°F	2%	20 g
30°C / 86°F	1%	10 g

### Preparation of the Equipment

Always work with clean mixing containers and application material.

### Application

Armour-Guard Primer S should be evenly distributed with a spatula or rubber squeegee and a short-haired paint roller. Apply enough primer to create a full coverage, unbroken film with no dry spots or puddles. Apply a second coat of Armour-Guard Primer S on highly porous surfaces. Extra mechanical adhesion can be obtained by broadcasting dry quartz into the uncured primer (0.5 kg/m<sup>2</sup>). Polyurethane and epoxy systems can be applied onto a fully broadcasted Armour-Guard Primer S. Do not disturb the paraffin layer that occurs during curing.

### Finishing

The cured primer can be overcoated after one hour (+20°C / 68°F) with the further Armour-Guard System to be installed.

### Application Conditions

Concrete should be at least 28 days old.

The recommended processing temperature for substrate, environment, material and products is between 0°C and +35°C / 32°F and 95°F. For temperatures lower than 0°C / 32°F please contact a Transpo regional manager for guidance.

Relative humidity: Max. 85%

Dew point: The temperature of the substrate and the applied product must be at least 3°C / 5°F higher than

the dew point, during application. Avoid condensation on the surface from the moment that the application starts until complete curing of the products. Ensure adequate ventilation and a low relative humidity during curing.

### Cleaning and Maintenance

Clean any used tools with MEK, acetone or m/ethyl acetate before the curing of Armour-Guard Primer S. Cured products residues must be removed mechanically.

### Complementary Products

- Cleaning solvent for tools: MEK or m/ethyl acetate
- Armour-Guard Catalyst

## TECHNICAL DATA

### Appearance — Composition

Liquid with low viscosity, colourless, slightly cloudy.

### Reaction Times

Processing time after mixing: 10 to 15 min.

Walkable: after 1 hour

Recoat: after 1 hour

Fully mechanical load: after 2 hours

Full chemical resistance: after 2 hours

Times measured at 20°C / 68°F; lower temperatures extend the curing time.

### Consumption

Consumption: 0.3-0.5 kg/m<sup>2</sup> / 130-80 ft<sup>2</sup>/gal

For porous surfaces the consumption will be higher.

### Technical Data

Odour	Methyl methacrylate (See also information sheet "Armour-Guard Odour")
Initiator: Armour-Guard Catalyst	BPO 6%, depending on the temperature from 1% to 6% weight calculated on the proportion of Armour-Guard Primer S
Viscosity	200 - 250 mPa.s (20°C Brookfield, spindle III/200 rpm)
Density	1 g/cm <sup>3</sup> ±0,1 (20°C / 68°F)
Flash point	10°C (MMA, DIN 51 755)
Exothermic peak	120–145°C / 248–293°F
<b>Armour-Guard Primer S + 2% Armour-Guard Catalyst</b>	
Density	0.98 g/cm <sup>3</sup>
Colour	Yellow-brown transparent
Shore D hardness	70–80

### Chemical Resistance

Polymerized Armour-Guard resins have good chemical resistance to alkalis, petroleum derivatives, acid, salts and maintenance products. Armour-Guard resins are not resistant to solvents. For more information please contact a Transpo regional manager.

### CE Marking



Transpo Industries

12

EN 13813

Synthetic resin floor/coating for indoor use in buildings

Release of corrosive substances	SR
Abrasion resistance	NDP
Bond strength	≥B2,0
Impact resistance	NDP
Reaction to fire	E <sub>fl</sub>

### Reference documents

Information sheet "Armour-Guard Odour."



FM 78518



## PACKAGING

### Armour-Guard Primer S

20 kg / 5.28 gal	Metal pail
180 kg / 47.55 gal	Drum

To be ordered separately:

### Armour-Guard Catalyst

10 kg / 22 lb	Plastic pail
25 kg / 55.1 lb	Plastic pail

## STORAGE AND SHELF LIFE

Store Armour-Guard products in a dry, well-ventilated storage area between +5°C and +35°C / 41°F and 95°F.

Shelf life: 12 months after production date.

In case of doubt, please contact Transpo and state the batch number on the packaging. Do not discharge into groundwater, surface water of sewers. Dispose of contaminated packaging and residues in accordance with the applicable legal requirements.

## SAFETY PRECAUTIONS

Please read the safety data sheets carefully before using Armour-Guard products. The products emit a characteristic odour during processing. Provide adequate ventilation. Keep away from sources of ignition. No smoking. Avoid skin contact. Eye irritation and/or hypersensitivity may occur at high vapour concentrations, upon inhalation and/or skin contact. Do not store food or beverages in the work area. Always wear personal protective equipment in accordance with all applicable local regulations and legislation. Gloves and safety goggles are mandatory.

**WARRANTY:** The following warranty is made in lieu of all other warranties, either expressed or implied. This product is manufactured of selected raw materials by skilled technicians. Neither seller nor manufacturer has any knowledge or control concerning the purchaser's use of either product and no warranty is made as to the results of any use. The only obligation of either seller or manufacturer shall be to replace any quantity of this product that proves to be defective. Neither seller nor manufacturer assumes any liability for injury, loss, or damage resulting from use of this product.